

# H-UKR application sheet

H-UKR cement is suitable in reinforced or unreinforced structures. It can be used in the following areas:

- Industrial buildings, collective housing, and individual houses: standard mortar masonry and standard concrete structures (foundations, slabs, posts, beams, wall ties, lintels, etc.)
- Civil engineering and mass concrete works: rafts for wind turbines, foundations, etc.
- Agricultural concrete: slurry pits, silos, and storage areas (fertilizer, manure, silage, etc.)
- Concrete for wastewater treatment plants
- Lightweight precast with appropriate heat treatment.

## Recommendations for use

- Pouring temperature: +5°C to +40°C.
- Ensure that equipment is clean before producing mortar or concrete.
- Do not mix H-UKR cement with any other material such as Portland cement, lime, etc.
- Aim for a Water/Cement ratio as low as possible, compatible with the consistency of the mortar/concrete for its use.
- Only use admixtures recommended by HOFFMANN GREEN CEMENT TECHNOLOGIES.
- For pouring horizontal surfaces, it is possible to add anti-crack fibers (glass fiber, cellulose, or polypropylene) to the mixture. Always use a curing product to prevent the concrete from drying out. Water curing is prohibited; commercial treatment products are suitable.
- Use appropriate personal protective equipment (PPE): pants, long-sleeved clothing, gloves, waterproof shoes, safety glasses, etc.
- Store bags of H-UKR cement in a dry location.



**HOFFMANN  
GREEN CEMENT**  
Catalyst of  
the Carbon  
Transition

# Properties

- Easy to use.
- Multipurpose cement for mortar and concrete.
- Appropriate usage time for implementation.
- Suitable for aggressive environments, such as marine and sulfated waters.
- Carbon footprint reduced by 85% compared to an OPC.
- Intended for all areas of construction applications.
- Concrete with a compressive strength class of 16 MPa [N/mm²] to 50 MPa [N/mm²] (on Cylindrical Concrete Specimens at 28 days)
- Made in France.

H-UKR COMPRESSIVE STRENGTH ACCORDING TO INTERNAL PROTOCOL

| Compressive Strength in MPa (N/mm2) |      |
|-------------------------------------|------|
| 7d                                  | 28d  |
| 52.0                                | 63.8 |

FORMWORK REMOVAL TIME GUIDELINES

| Average temperature   | Time required for removing from structures after pouring |
|-----------------------|----------------------------------------------------------|
| Between 20°C and 40°C | The day after                                            |
| Between 15°C and 20°C | The day after                                            |

## RECOMMENDED QUANTITIES FOR MORTAR AND CONCRETE COMPOSITIONS INTENDED FOR MASONRY WORK.

It is important to comply with the quantities and professional standards for implementation

| Quantity for one 25-kg bag of H-UKR cement | Equivalent quantity of cement | Sand 0/4 mm | Gravel 4/10 mm to 4/20 mm | Water       | Mixing Volume |
|--------------------------------------------|-------------------------------|-------------|---------------------------|-------------|---------------|
| Masonry concrete                           | 350 kg/m³                     | 4 buckets   | 5 buckets                 | ≈ 12 liters | ≈ 70 liters   |
| Masonry mortar                             | 300 kg/m³                     | 8 buckets   | -                         | ≈ 20 liters | ≈ 80 liters   |
|                                            | 350 kg/m³                     | 7 buckets   | -                         | ≈ 17 liters | ≈ 70 liters   |
| Traditional screed mortar (dry)            | 300 kg/m³                     | 8 buckets   | -                         | ≈ 14 liters | ≈ 85 liters   |
|                                            | 350 kg/m³                     | 7 buckets   | -                         | ≈ 12 liters | ≈ 75 liters   |
| Paving mortar                              | 250 kg/m³                     | 10 buckets  | -                         | ≈ 25 liters | ≈ 100 liters  |
|                                            | 300 kg/m³                     | 8 buckets   | -                         | ≈ 20 liters | ≈ 80 liters   |

The quantities are given for information purposes only. They may vary depending on the mineralogical nature and characteristics of the sand and gravel used.  
Water quantities are mentioned for sand and dry gravel. The quantity of water to use during mixing must be adapted according to the humidity of the sand and gravel.  
1 bucket = 10 liters

See all the information on H-UKR by scanning this QR code.



For all requests, you can contact our teams by scanning this QR code:



Find us on [www.ciments-hoffmann.com](http://www.ciments-hoffmann.com)